

The test results show that sample contains only natural latex and contains no fillers. The filler content is calculated as the difference in amount of ash and zinc oxide, assuming that the maximum of zinc oxide is less than 5% of the total latex foam.

0 0	Natural Rubber share	Styrene-Butadiene Rubber share	Ash content / share	Filler content / share
Natural Vita Talalay	<b>97</b> %	0%	3%	0%
Natural Vita Talalay Origins	96%	0%	4%	0%

Geleen, 6-11-2020, Jeroen Welzen – Experienced Professional Chemical Analysis



**NEW CONNECTIONS • NEW SOLUTIONS**